

• Seamless steel tubes for drilling

試すい用継目無鋼管

JIS G 3465

(非JIS認証対象品)

| 種類の記号    | 化学成分   |        | 引張試験「TP=JIS11号」   |                   |     | 製造方法  | 仕上方法               |
|----------|--------|--------|-------------------|-------------------|-----|-------|--------------------|
|          | P      | S      | 引張強さ              | 降伏点               | 伸び  |       |                    |
| 単位       | %      | %      | N/mm <sup>2</sup> | N/mm <sup>2</sup> | %   |       |                    |
| STM-C540 | ≦0.040 | ≦0.040 | ≧540              | -                 | ≧18 | S-C*1 | 冷間仕上げのまま、または適切な熱処理 |
| STM-C640 |        |        | ≧640              | -                 | ≧16 |       |                    |
| STM-R590 |        |        | ≧590              | ≧375              | ≧18 |       |                    |
| STM-R690 |        |        | ≧690              | ≧440              | ≧16 |       |                    |
| STM-R780 |        |        | ≧780              | ≧520              | ≧15 |       |                    |
| STM-R830 |        |        | ≧830              | ≧590              | ≧10 |       |                    |

\*1 S-C: 冷間仕上継目無鋼管